

Product Specification

Product Code	RBLPS003
Description	50 -114mm x 4mm Round Solid Section Black Plastic lollipop Sticks
Packaging	Packed in retail packs of 50 with a choice of 2 bags types – -Official Yolli -Clear Unbranded
Material	HIPS (High Impact Poly Styrene) HI 425E
Colour	Deep Black OM0055P
Length Tolerance +/-	1mm
Diameter Tolerance +/- %	3.5
Pack Quantity	50 Pieces
Count Tolerance +/- %	2
Pack Weight Tolerance +/- %	2.5
Suggested Uses	Lollipops, Cake pops Arts and Crafts
Warnings	-Lollipop sticks are a potential choking hazard and are not suitable for children under the age of 3 years. Children under the age of 5 years should be supervised at all times when using lollipop sticks. -Plastic Lollipop sticks are not suitable for oven use – softening point 98° C

Technical Data Sheet

HIPS(High Impact Poly Styrene)

HI 425E

Features	High strength extrusion
Applications	Disposable cups, Food packing sheet, Wrapping films, Trays, Washing machines

Physical	Test Method	Value
Density	ASTM D792	1.03 g/cm ³
Melt Flow Index (200°C, 5kg)	ASTM D1238	4.5 g/10min
Mold Shrinkage	ASTM D955	0.3 ~ 0.6 %
Water absorption	ASTM D570	0.03 %

Mechanical	Test Method	Value
Tensile Strength	ASTM D638	280 kg/cm ² (3,976) (psi)
Elongation	ASTM D638	55 %
Flexural Strength	ASTM D790	350 kg/cm ² (4,970) (psi)
Flexural Modulus	ASTM D790	17,500 kg/cm ² (248,500) (psi)
Izod Impact Strength(3.2mm)	ASTM D256	9.5 kgcm/cm (1.76) (ft-lb/in)
Rockwell Hardness(L scale)	ASTM D785	65

Thermal	Test Method	Value
Heat Deflection Temperature(18.6kgf/cm ²)	ASTM D648	80 °C (176) (°F)
Vicat Softening Temperature(1kg, 50°C/h)	ASTM D1525	98 °C (208) (°F)

Flammability	Test Method	Value
Flame Rating - UL (1.6mm)	UL 94	HB

Notes

These are just typical properties, not specifications. Users should confirm results by their own test.

Technical Data Sheet

HIPS(High Impact Poly Styrene)

HI 425E

Processing guide

Injection Guide	Unit	Value
Nozzle	°C	190~220
Front	°C	190~210
Middle	°C	180~200
Rear	°C	170~190
Hopper Throat	°C	45
Mold	°C	40~60

Extrusion Guide	Unit	Value
Zone 1	°C	170~190
Zone 2	°C	180~200
Zone 3	°C	180~210
Zone 4	°C	190~220
Zone 5	°C	200~220
Screen Changer	°C	190~210
Adaptor	°C	200
Die	°C	190~210

Drying	Unit	Value
Temperature	°C	60~70
Time	hr	1~3

Notes

These are only mentioned as general guidelines.

Safety Data Sheet in accordance with Regulation (EU)**No.453/2010****OMNICOLOR Deep Black OM0055P**

Page 1(9)

Substance key: 000000365207
Version : 1 - 4 / GBRevision Date: 06.02.2012
Date of printing : 24.04.2012**SECTION 1: Identification of the substance/mixture and of the company/undertaking****1.1. Product identifier****Trade name****OMNICOLOR Deep Black OM0055P****Material number:** OM90235000**1.2. Relevant identified uses of the substance or mixture and uses advised against****Relevant identified uses of the substance or mixture**Industry sector : Plastic processing industry.
Type of use : Additive for plastic material processing**1.3. Details of the supplier of the safety data sheet****Identification of the company**

Clariant Masterbatches Ireland

Monread Industrial Estate

Naas

Telephone no. : +353 45 866565

Information about the substance/mixture

Product Stewardship

BU Masterbatches

e-mail: PSE.MB.DE@clariant.com

1.4. Emergency telephone number

00800-5121 5121 (24 h)

SECTION 2: Hazards identification**2.1. Classification of the substance or mixture****Classification according EC Directive (67/548/EEC or 1999/45/EC, as amended)**

The product is not classified as dangerous according to EC directives/the relevant national laws.

hazard warning labelling not compulsory

2.2. Label elements**Labelling in accordance with EC-Directives (67/548/EEC or 1999/45/EC, as amended)**

The product does not require a hazard warning label in accordance with EC directives/the relevant national laws.

2.3. Other hazards

Spilled granules give rise to a slipping hazard. Clean up immediately.

Safety Data Sheet in accordance with Regulation (EU)**No.453/2010****OMNICOLOR Deep Black OM0055P**

Page 2(9)

Substance key: 000000365207
Version : 1 - 4 / GBRevision Date: 06.02.2012
Date of printing : 24.04.2012**SECTION 3: Composition/information on ingredients****3.2. Mixtures****Chemical characterization**Colourant preparation
Carrier: Mixture**SECTION 4: First aid measures****4.1. Description of first aid measures****General information**

No special measures necessary.

After contact with skinAfter contact with molten product cool quickly with cold water
Do not pull solidified product from skin
Take for medical treatment**After contact with eyes**Begin with medical treatment.
In case of contact with eyes remove the product and rinse thoroughly with water.**After ingestion**Do not induce vomiting.
Call in a physician immediately and show him the Safety Data Sheet.**4.2. Most important symptoms and effects, both acute and delayed****Symptoms**

No significant symptom known, only those caused by the physical form of the material.

4.3. Indication of any immediate medical attention and special treatment needed**Treatment**

In case of problems seek medical advice and show the package or label

SECTION 5: Firefighting measures**5.1. Extinguishing media****Suitable extinguishing media**water spray jet
foam
carbon dioxide
dry powder**Extinguishing media that must not be used for safety reasons**

Full water jet

5.2. Special hazards arising from the substance or mixture

Safety Data Sheet in accordance with Regulation (EU)

No.453/2010

OMNICOLOR Deep Black OM0055P

Page 3(9)

Substance key: 000000365207
Version : 1 - 4 / GB

Revision Date: 06.02.2012
Date of printing : 24.04.2012

In case of fires, hazardous combustion gases are formed:
Carbon monoxide (CO)
Carbon dioxide (CO₂)
Under certain conditions of combustion traces of other toxic substances cannot be excluded

5.3. Advice for firefighters

Special protective equipment for firefighting

Use self-contained breathing apparatus

SECTION 6: Accidental release measures

6.1. Personal precautions, protective equipment and emergency procedures

See: Exposure controls and personal protection.
High risk of slipping if leaked/spilled product is not cleaned up.

6.2. Environmental precautions

Do not allow to enter drains or waterways

6.3. Methods and material for containment and cleaning up

Spillage should be swept up immediately.
Pick up mechanically.

6.4. Reference to other sections

Additional information

Information regarding personal protective measures see, chapter 8.

SECTION 7: Handling and storage

7.1. Precautions for safe handling

Advice on safe handling

Ensure good general ventilation in the workplace; local exhaust ventilation may be necessary, especially when emptying containers.

Hygiene measures

The usual Industrial Hygiene precautions must be taken during work, in particular: do not drink, eat or smoke during the handling of the product and clean hands and face during work intervals and after work.

Advice on protection against fire and explosion

Take precautions against accumulation of electrostatic charge

7.2. Conditions for safe storage, including any incompatibilities

Requirements for storage areas and containers

Keep container tightly closed in a cool, well-ventilated place.
Protect from moisture.
Protect from direct sunlight

Safety Data Sheet in accordance with Regulation (EU)

No.453/2010

OMNICOLOR Deep Black OM0055P

Page 4(9)

 Substance key: 000000365207
 Version : 1 - 4 / GB

 Revision Date: 06.02.2012
 Date of printing : 24.04.2012

Advice on storage compatibility

Not required.

7.3. Specific end use(s)

No further recommendations.

SECTION 8: Exposure controls/personal protection

8.1. Control parameters

Exposure limit values

 Carbon black
 EC number: 215-609-9
 CAS number : 1333-86-4

Regulatory basis / Regulatory list	Revision	Type of value	Values	Remarks
EH40 WELs (amended) UK OEL - EH40 WELs	01/01/2007	Long-term exposure limit (8-hour TWA reference period)	3.5 mg/m ³	
EH40 WELs (amended) UK OEL - EH40 WELs	01/01/2007	Short term exposure limit - 15 mins.	7 mg/m ³	

 Vinyl acetate
 EC number: 203-545-4
 CAS number : 108-05-4

Regulatory basis / Regulatory list	Revision	Type of value	Values	Remarks
Directive on indicative exposure limits (amended) EU OEL - Directive on indicative exposure limits	01/01/2009	Short Term Exposure Level	35.2 mg/m ³ 10 ppm	

 Acetic acid
 EC number: 200-580-7
 CAS number : 64-19-7

Regulatory basis / Regulatory list	Revision	Type of value	Values	Remarks
Directive on indicative exposure limits (amended) EU OEL - Directive on indicative exposure limits	29/05/1991	Threshold Limit Values	25 mg/m ³ 10 ppm	

DNEL/DMEL values

DNEL/DMEL values are not available.

PNEC values

PNEC values are not available.

8.2. Exposure controls

Safety Data Sheet in accordance with Regulation (EU)

No.453/2010

OMNICOLOR Deep Black OM0055P

Page 5(9)

Substance key: 000000365207
Version : 1 - 4 / GB

Revision Date: 06.02.2012
Date of printing : 24.04.2012

General protective measures

Observe precautions disposal of Directive 89/686/EEC and following amendments regarding individual protection equipment for handling materials in the chemistry industry.

Respiratory protection : In case of insufficient exhaust ventilation or prolonged exposure use respiratory protection equipment according to EEC-directive 89/686

Hand protection : Leather gloves
Nitrile rubber gloves.
Minimum thickness (glove): valid statement not possible.
Minimum breakthrough time (glove): valid statement not possible.

These types of protective gloves are offered by various manufacturers. Please note the manufacturers' detailed statements, especially about the minimum thickness and the minimum breakthrough time. Consider also the particular working conditions under which the gloves are being used.

Eye protection : safety glasses

SECTION 9: Physical and chemical properties

9.1. Information on basic physical and chemical properties

Physical state : solid

Form : Granules

Particle size : Product specific

Colour : black

Odour : characteristic

Odour threshold : cannot be determined

pH value : Not applicable

Melting point : not determined

Boiling point : not applicable

Flash point : Not applicable

Evaporation rate : This information is not applicable for solids.

Flammability

Lower explosion limit : not tested.

Upper explosive limit : not tested.

Vapour pressure : Not applicable

Vapour density relative to air : This information is not applicable for solids.

Relative Density: not available

Solubility in water : insoluble

Safety Data Sheet in accordance with Regulation (EU)**No.453/2010****OMNICOLOR Deep Black OM0055P**

Page 6(9)

Substance key: 000000365207
Version : 1 - 4 / GBRevision Date: 06.02.2012
Date of printing : 24.04.2012

Octanol/water partition coefficient (log Pow) :	This property is not applicable for mixtures.
Self-ignition temperature :	Not applicable
Thermal decomposition :	To the best of our current knowledge, no thermal decomposition of the product is expected if it is processed according to good manufacturing practices.
Viscosity (dynamic) :	Not applicable
Viscosity (kinematic) :	Not applicable
Explosive properties :	Explosive according to EU supply regulations : no data Explosive according transport regulation : no data
Oxidizing properties :	not available

9.2. Other information

Density :	not tested.
Surface tension :	not relevant for safety
Thermal conductivity :	not tested.
Specific resistance / electrical conductivity :	not tested.
Further information	
Explosion hazard:	Not an explosion hazard.

SECTION 10: Stability and reactivity**10.1. Reactivity**

See section 10.3. "Possibility of hazardous reactions"

10.2. Chemical stability

Stable.

10.3. Possibility of hazardous reactions

No hazardous reactions when stored and handled according to prescribed instructions.

10.4. Conditions to avoid

Temperatures exceeding thermal stability of the masterbatch. Electrostatic charges.

10.5. Incompatible materials

not known

10.6. Hazardous decomposition products

No decomposition if used as intended.

Safety Data Sheet in accordance with Regulation (EU)**No.453/2010****OMNICOLOR Deep Black OM0055P**

Page 7(9)

Substance key: 000000365207
Version : 1 - 4 / GBRevision Date: 06.02.2012
Date of printing : 24.04.2012**SECTION 11: Toxicological information****11.1. Information on toxicological effects****Information related to the product itself:**

Acute oral toxicity : LD50 > 2,000 mg/kg (rat)
The product has not been tested. The information is derived from the properties of the individual components.

Irritant effect on skin : non-irritant

Irritant effect on eyes : non-irritant

Sensitization : non-sensitizing

Remarks

Determined on raw material components in accordance with Directive 1999/45/EC.

SECTION 12: Ecological information**12.1. Toxicity****Information related to the product itself:**

Fish toxicity : No data available.

12.2. Persistence and degradability**Information related to the product itself:**

Physico-chemical eliminability : The product can be separated out mechanically.

12.3. Bioaccumulative potential**Information related to the product itself:**

Bioaccumulation: not tested.

12.4. Mobility in soil**Information related to the product itself:**

Transport and distribution between environmental compartments : not tested.

12.5. Results of PBT and vPvB assessment**Information related to the product itself:**

No information is available as no chemical safety report (CSR) is required.

12.6. Other adverse effects**Information related to the product itself:**

Safety Data Sheet in accordance with Regulation (EU)**No.453/2010****OMNICOLOR Deep Black OM0055P**

Page 8(9)

Substance key: 000000365207
Version : 1 - 4 / GBRevision Date: 06.02.2012
Date of printing : 24.04.2012**Additional ecotoxicological remarks**

Do not allow to enter ground water, waterways or waste water.

SECTION 13: Disposal considerations**13.1. Waste treatment methods****Product**

Residual chemical should be subjected to waste management, using an approved waste disposal contractor, in compliance with EC regulations 91/156/EEC; 91/689/EEC; 94/62/EC and subsequent amendments

Uncleaned packaging

Contaminated packaging material should be treated equivalent to residual chemicals. Clean packaging material should be subjected to waste management schemes (recovery recycling, reuse) according to local legislation.

SECTION 14: Transport information**Section 14.1. to 14.5.**

ADR	not restricted
ADN	not restricted
RID	not restricted
IATA	not restricted
IMDG	not restricted

14.6. Special precautions for user

See sections 6 to 8 of this Safety Data Sheet.

14.7. Transport in bulk according to Annex II of MARPOL73/78 and the IBC Code (International Bulk Chemicals Code)

No transport as bulk according IBC - Code.

SECTION 15: Regulatory information**15.1. Safety, health and environmental regulations/legislation specific for the substance or mixture****Other regulations**

All the ingredients of the preparation comply with the applicable requirements of the current REACH Regulation.

15.2. Chemical safety assessment

No Chemical Safety Assessment (CSA) is yet available for the component substances of this preparation.

Safety Data Sheet in accordance with Regulation (EU)**No.453/2010****OMNICOLOR Deep Black OM0055P**

Page 9(9)

Substance key: 000000365207
Version : 1 - 4 / GBRevision Date: 06.02.2012
Date of printing : 24.04.2012**SECTION 16: Other information**

This information corresponds to the present state of our knowledge and is intended as a general description of our products and their possible applications. Clariant makes no warranties, express or implied, as to the information's accuracy, adequacy, sufficiency or freedom from defect and assumes no liability in connection with any use of this information. Any user of this product is responsible for determining the suitability of Clariant's products for its particular application. Nothing included in this information waives any of Clariant's General Terms and Conditions of Sale, which control unless it agrees otherwise in writing. Any existing intellectual/industrial property rights must be observed. Due to possible changes in our products and applicable national and international regulations and laws, the status of our products could change. Material Safety Data Sheets providing safety precautions, that should be observed when handling or storing Clariant products, are available upon request and are provided in compliance with applicable law. You should obtain and review the applicable Material Safety Data Sheet information before handling any of these products. For additional information, please contact Clariant.

File No. : QA-2012-106

Issued Date : May. 07, 2012

Receive :

Reference :

Title : Food statement on Regulation (EU) No 10/2011

Product Information

Grade : HI 425E

Our mentioned product contains substances listed in authorised monomers and other starting substances, additives and polymer production aids of ANNEX I of Commission Regulation (EU) No 10/2011 on plastic materials and articles in contact with food.

- The Monomers and other starting substances listed in ANNEX I
 - Butadiene, CAS No 106-99-0, SML = not detectable
 - Styrene, CAS No 100-42-5

The product does not contain substances authorized as food additives or flavouring with restrictions in the applicable EC directives.

Quality Assurance Manager
Cheol Hee Yoon





Test Report

No.HKHL1303021955JL

Date: MAR 20, 2013

Page 1 of 4

KUMHO PETROCHEMICAL CO.,LTD.
#45-25, SEONGNAM -DONG, NAM-GU, ULSAN 680-140, KOREA

The following samples were submitted and identified on behalf of the client as:

HI 425E

SGS Case No. : HKHL130300012375
SGS Ref No. : AYAA13-10508

Sample Receiving Date : MAR 04, 2013
Test Performing Date : MAR 04 – 19, 2013

Test Requested : Please refer to the result summary.

Test Method & Results : Please refer to next page(s).

Result Summary :

Test Requested	Conclusion
1. German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 31.	--
Sensorial examination odour and taste test	PASS
2. German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30, European Commission Regulation (EU) No 10/2011 and BfR recommendation.	--
Plastic – Lead and Cadmium	PASS
3. European Commission Regulation (EU) No 10/2011	--
a) Plastic – Overall migration	PASS
b) Plastic – Specific Migration of Heavy Metals	PASS

Signed for and on behalf of
SGS Hong Kong Ltd.

Che Wai Leuk, Jerry
Section Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.





Test Report

No.HKHL1303021955JL

Date: MAR 20, 2013

Page 2 of 4

Test Results :

1. German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 31.

Sensory examination – odour and taste test

Method : With reference to DIN10955:2004-06.

Test Item	Result	Permissible Limit
	1	
Sensorial examination odour (Intensity scale)	1.0	2.5
Sensorial examination taste (Intensity scale)	1.0	2.5
Comment	PASS	--

Sample Description :

1. White Plastic

Note : Intensity scale :

- 0 – no perceptible deviation
- 1 – deviation just perceptible
- 2 – moderate deviation
- 3 – distinct deviation
- 4 – large deviation

2. German Food, Articles of Daily Use and Feed Code of September 1, 2005 (LFGB), Section 30, European Commission Regulation (EU) No 10/2011 and BfR recommendation.

Plastic – Lead and Cadmium

Method : i) Lead content : Acid digestion followed by analysis with Atomic Absorption Spectrometry.
ii) Cadmium content : With reference to EN 1122:2001, Method B

Test Item	Result (mg/kg)	Reporting Limit (mg/kg)	Reference Limit (mg/kg)
	1		
Lead content	ND	2	Absent
Cadmium content	ND	2	Absent
Comment – Lead and Cadmium	PASS	--	--

Sample Description :

1. White Plastic

Note : 1. Lead and Cadmium content: mg/kg = milligram per kilogram

2. ND = Not Detected

3. When lead or/and cadmium is/are found to be present but feasibly low in value to migrate, migratable lead or cadmium will be determined to evaluate its compliance.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Test Results (Con't) :

3. European Commission Regulation (EU) No 10/2011

a) Plastic – Overall migration

Method : With reference to EN 1186-1:2002 for selection of conditions and test methods;
 EN 1186-3:2002 aqueous food simulants by total immersion method;
 EN 1186-2:2002 olive oil by total immersion method;

Simulant Used	Test Condition	Result (mg/dm ²)	Reporting Limit (mg/dm ²)	Permissible Limit (mg/dm ²)
		1		
3% Acetic Acid (W/V) Aqueous Solution	10 days at 40°C	ND	3.0	10
50% Ethanol (V/V) Aqueous Solution	10 days at 40°C	ND	3.0	10
Rectified Olive Oil	10 days at 40°C	ND	3.0	10
Comment	--	PASS	--	--

Sample Description :

1. White Plastic

Note : 1. mg/dm² = milligram per square decimeter
 2. °C = degree Celsius
 3. ND = Not Detected

Remark :

1. Test condition & simulant were specified by client.

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Test Results (Con't) :

b) Plastic – Specific Migration of Heavy Metals

Method: Sample preparation in 3% acetic acid (w/v) in aqueous solution at 40°C for 10 days with reference to EN 13130-1:2004; followed by analysis using Inductively Coupled Argon Plasma Spectrometry (ICP).

Test Item	Result (mg/kg)	Reporting Limit (mg/kg)	Permissible Limit (mg/kg)
	1		
Specific Migration of Barium	ND	0.25	1
Specific Migration of Cobalt	ND	0.03	0.05
Specific Migration of Copper	ND	0.25	5
Specific Migration of Iron	ND	0.25	48
Specific Migration of Lithium	ND	0.5	0.6
Specific Migration of Manganese	ND	0.25	0.6
Specific Migration of Zinc	ND	0.5	25
Comment	PASS	--	--

Sample Description :

1. White Plastic

- Note :
1. mg/kg = milligram per kilogram of foodstuff in contact with
 2. °C = degree Celsius
 3. ND = Not Detected

Remark :

1. Test condition & simulatant were specified by client.



*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.